



Werkstoffe

Gegenring: Keramik (C)
SIC (U31)

Elastomer: PTFE (T)

d ₁	b	c	g	m
19	36,4	47	4,8	8,0
20	39,6	50	4,8	8,0
22	39,6	50	4,8	8,0
24	42,7	53	4,8	8,0
25	42,7	53	4,8	8,0
28	50,7	63	8,0	11,0
30	53,9	66	8,0	11,0
32	53,9	66	8,0	11,0
33	57,0	69	8,0	11,0
35	57,0	69	8,0	11,0
38	63,4	76	8,0	11,0
40	66,5	79	8,0	11,0
43	69,7	82	8,0	11,0
45	69,7	82	8,0	11,0
48	79,3	95	9,5	14,3
50	79,3	95	9,5	14,3
53	82,4	98	9,5	14,3
55	85,6	101	9,5	14,3
58	88,8	106	9,5	14,3
60	88,8	106	9,5	14,3
63	91,9	108	9,5	14,3
65	95,1	111	9,5	14,3
68	98,3	114	9,5	14,3
70	98,3	114	9,5	14,3
75	103,1	119	9,5	14,3